

SUNKEM QUICKSET

DESCRIPTION

Ready to use quick setting colourless liquid. It promotes rapid hardening and early gain of strength of neat cement paste. It exhibits setting time of OPC within 4 to 6 minutes depending upon freshness of cement.

USES

For sealing joints in masonry. cracks in rock tunnels, to stop less severe infiltration of water. In moderate leakage, it is found quite effective specially in underground concrete structures.

METHOD OF APPLICATION

Mix 1 part of Quickset with 3 parts of OPC by volume within 30 seconds and then place it and work on the leaking areas.

CONSUMPTION RATE

Approx 12 litter per 50 kg cement or 16 to 17 kg per 50 kg cement (ref. technical data sheet for further information)

PACK SIZE

5kg, 10 kg, 20 kg H.D.P.E. container.

